



شرکت کاسپین پلیمر
تولید کننده انواع استابلایزر و روان کننده های صنعتی

Caspian Polymer Co.

Technical Data Sheet

Stearic Acid

Code: CSAL-206

Description:

Palm Stearic Acid, Cosmetic Grade

Specification:

Appearance:	Super White, Beads / Flakes
Acid Value:	205 – 211
Saponification Value:	206 – 211
Iodine Value:	0.5 Max.
Color Lov 5¼" Cell, R / Y:	0.5 / 5 Max.
Titre, Deg C:	54 – 57
% C12 Luaric Acid:	1 Max.
% C14:0 Myristic Acid:	2 Max.
% C16:0 Palmitic Acid:	49 – 58
% C18:0 Stearic Acid:	40 – 48
% C18:1 Oleic Acid:	1 Max.
Other:	1 Max.

Area of Application:

For industrial application in the manufacturing of Pharmaceutical and Cosmetic, PVC compounding, Tyre, Rubber Products, Resins, Emulsion Polymer, Stabilizers, Candle, Lubricants, Grease, Coatings, food packaging and etc.

Recommended Mix:

Depending on method of production and formulation it would vary.

Packing Details:

Lined with a 25kg Polypropylene bag

www.caspian-polymer.com

E-mail : info@caspian-polymer.com
Sales : marketing@caspian-polymer.com
Management : Management@caspian-polymer.com

Hafez St, Dekhoda Blvd, Caspian Industrial Town, Qazvin-IRAN
Tel : (+98) 283 284 81 50 - 2 Fax : (+98) 283 284 81 53